

formlabs Form 4B IBT Flex Resin



formlabs Form 4B IBT Flex Resin Instructions

[Home](#) » [formlabs](#) » formlabs Form 4B IBT Flex Resin Instructions 

Contents

- 1 [formlabs Form 4B IBT Flex Resin](#)
- 2 [Product Usage Instructions](#)
- 3 [Specific Manufacturing Considerations](#)
- 4 [PRINTING](#)
- 5 [PART REMOVAL](#)
- 6 [WASHING](#)
- 7 [DRYING](#)
- 8 [POST-CURING](#)
- 9 [SUPPORT REMOVAL & POLISHING](#)
- 10 [CLEANING & DISINFECTION](#)
- 11 [FAQ](#)
- 12 [Documents / Resources](#)
 - 12.1 [References](#)
- 13 [Related Posts](#)



formlabs Form 4B IBT Flex Resin



Specifications

- **Product Name:** IBT Flex Resin
- **Type:** Light-curable polymer-based resin
- **Intended Use:** Additive fabrication of biocompatible, short-term use, removable dental appliances
- **Applications:** Indirect bonding trays, trays for guided restorative techniques

Product Usage Instructions

Specific Manufacturing Considerations

- **Hardware:** Formlabs 3D Printer – Form 3B/3B+, Form 3BL, Form 4B
- **Print Accessories:** Formlabs Build Platforms, Resin Tanks
- **Software:** Formlabs PreForm
- **Printing Parameters:**
 - **Part Thickness:** Minimum 1 mm
- **Recommended Post-Processing Equipment:**
 - Resin Pumping System
 - Form Wash, Form Wash (2nd Generation), Form Wash L
 - Form Cure, Form Cure L, Fast Cure

Printing

1. **Shake Cartridge:** Shake before every print job to avoid color deviations and print failures.
2. **Set up:** Insert resin cartridge into the printer, add resin tank, and attach mixer.
3. **Printing Steps:**
 1. Prepare job using PreForm software, import STL file.
 2. Orient and generate supports if needed.
 3. Send job to printer.

4. **Optional:** Pre-fill tank if empty.
5. Select print job and follow prompts on the screen.

Part Removal

Remove build platform and wedge part removal tool under the printed part raft to rotate and remove parts. Visit support.formlabs.com for detailed techniques.

Washing

Place printed parts in a Formlabs-validated wash unit with 99% Isopropyl Alcohol (IPA).

1. For Form Wash, Form Wash (2nd Generation) – High speed*, or

Form Wash L:

- Wash for 20 minutes, then rinse parts with fresh IPA or soak in fresh IPA for 10 minutes.
- If parts are not clean, replace used Isopropyl Alcohol with fresh solvent.

IBT Flex Resin is a light-curable polymer-based resin designed for the additive fabrication of biocompatible, short-term use, removable dental appliances such as indirect bonding trays and trays for guided restorative techniques. This Manufacturing Guide will give equipment, printing, and post-processing recommendations and requirements to ensure the correct and safe usage of this material.

Specific Manufacturing Considerations

IBT Flex Resin specifications have been validated using the hardware and parameters indicated below. For biocompatibility compliance, validation used a dedicated resin tank, build platform, wash unit and post-processing equipment that were not mixed with any other resins.

1. Hardware:

1. Formlabs 3D Printer: Form 3B/3B+, Form 3BL, Form 4B
2. Print Accessories: Formlabs Build Platforms, Formlabs Resin Tanks

2. Software:

1. Formlabs PreForm

3. Printing Parameters:

1. Layer Thickness:

- **Form 3B/3B+:** 50 µm, 100 µm, 200 µm
- **Form 3BL:** 100 µm
- **Form 4B:** 50 µm, 100 µm

2. Part Orientation:

- **For 50 µm and 100 µm Print Settings:** Parts may be printed flat on the build platform without supports. If desired, parts may be printed on supports at up to a 40° tilted angle, with the intaglio surface facing away from the build platform.
- **For 200 µm Print Settings:** Print parts flat on the build platform without supports.

3. Part Thickness: 1 mm minimum

4. Recommended Post-Processing Equipment and Accessories:

1. **Formlabs Processing Accessories:** Resin Pumping System
2. **Formlabs Validated Wash Unit:** Form Wash, Form Wash (2nd Generation), Form Wash L
3. **Formlabs Validated Cure Unit:** Form Cure, Form Cure L, Fast Cure

PRINTING

1. **Shake cartridge:** Shake the cartridge before every print job. Color deviations and print failures may occur if the cartridge is shaken insufficiently.
2. **Set up:** Insert resin cartridge into a compatible Formlabs 3D printer. Insert resin tank and attach mixer to the tank.
3. **Printing:**
 1. Prepare a print job using PreForm software. Import desired part STL file.
 2. Orient and generate supports if needed.
 3. Send the print job to the printer.
 4. **Optional:** If starting with an empty resin tank, save time by manually pre-filling the tank by pouring in resin directly from the cartridge.
 5. Begin print by selecting a print job from the print menu. Follow any prompts or dialogs shown on the printer screen. The printer will automatically complete the print.

PART REMOVAL

Remove the build platform from the printer. To remove parts from the build platform, wedge the part removal tool under the printed part raft, and rotate the tool. For detailed techniques visit support.formlabs.com.

WASHING

Place the printed parts in a Formlabs-validated wash unit with 99% Isopropyl Alcohol (IPA).

1. Form Wash, Form Wash (2nd Generation) – High speed*, or Form Wash L:
 1. Wash for 20 minutes in the wash unit, then either rinse down parts completely with fresh IPA from a spray bottle, or soak parts in fresh IPA for 10 minutes.
 2. If parts do not appear clean after washing, consider replacing used Isopropyl Alcohol in the wash unit with fresh solvent.

For Form Wash (2nd Gen), High speed settings are validated for use.

DRYING

1. Remove parts from Isopropyl Alcohol and leave to air dry at room temperature for at least 30 minutes. NOTE: Dry times can vary depending on the design of parts and ambient conditions. Do not let parts sit in Isopropyl Alcohol for longer than needed.
2. Inspect printed parts to ensure that parts are clean and dry. No residual solvent, excess liquid resin or residue particles should remain on the surface before proceeding to subsequent steps.
3. If the residual solvent is still present, dry parts longer. If resin residue is still visible, rewash parts until clean and dry.

POST-CURING

Place the printed parts in a Formlabs-validated post-curing unit and cure for the required time.

1. Form Cure or Form Cure L:

1. Submerge parts in a transparent, water filled container. Place the container inside the cure unit, and cure for 30 minutes at 70 °C.
2. Allow the cure unit to cool down to room temperature between cure cycles.

2. Fast Cure:

1. Submerge parts in a transparent, water filled container. Place the container inside the cure unit, and cure for 5 minutes at Light Intensity 9
2. Allow the Fast Cure unit to cool for at least 10 minutes between cure cycles.

SUPPORT REMOVAL & POLISHING

1. Remove supports, with assistance of cutting pliers or other appropriate finishing tools as needed.
2. Inspect the parts for any cracks. Discard if any damage or cracks are detected.

CLEANING & DISINFECTION

1. Parts may be cleaned and disinfected according to facility protocols. Tested disinfection method: soaking the finished part in fresh 70% IPA for 5 minutes. Do not leave the part in the alcohol solution for longer than 5 minutes.
2. After cleaning and disinfection, inspect the part for damage or cracks to ensure that the integrity of the designed part meets performance requirements. Discard if any damage or cracks are detected.

ADDITIONAL REQUIREMENTS AND RECOMMENDATIONS FOR USAGE

For trays used for guided restorative techniques, apply a separating agent to reduce the adhesion of the tray to composite materials.

HAZARDS, STORAGE & DISPOSAL

1. Cured resin is non-hazardous and may be disposed of as regular waste.
2. See SDS for more information at support.formlabs.com.

FAQ

• Q: Can I use a different 3D printer with IBT Flex Resin?

A: The resin specifications have been validated only with Formlabs printers for optimal performance and safety.

• Q: How should I store the resin cartridge when not in use?

A: Store the cartridge in a cool, dry place away from direct sunlight to maintain its quality.

• Q: Is there a shelf life for IBT Flex Resin?

A: Yes, the resin has a shelf life. Check the product packaging for specific expiration dates.

Documents / Resources

MANUFACTURING GUIDE

IBT Flex Resin

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

61

62

63

64

65

66

67

68

69

70

71

72

73

74

75

76

77

78

79

80

81

82

83

84

85

86

87

88

89

90

91

92

93

94

95

96

97

98

99

100

101

102

103

104

105

106

107

108

109

110

111

112

113

114

115

116

117

118

119

120

121

122

123

124

125

126

127

128

129

130

131

132

133

134

135

136

137

138

139

140

141

142

143

144

145

146

147

148

149

150

151

152

153

154

155

156

157

158

159

160

161

162

163

164

165

166

167

168

169

170

171

172

173

174

175

176

177

178

179

180

181

182

183

184

185

186

187

188

189

190

191

192

193

194

195

196

197

198

199

200

formlabs

[formlabs Form 4B IBT Flex Resin](#) [pdf] Instructions

Form 4B IBT Flex Resin, Form 4B, IBT Flex Resin, Flex Resin, Resin

References

- [🦋 customer_v2](#)
- [User Manual](#)

[Manuals+](#), [Privacy Policy](#)

This website is an independent publication and is neither affiliated with nor endorsed by any of the trademark owners. The "Bluetooth®" word mark and logos are registered trademarks owned by Bluetooth SIG, Inc. The "Wi-Fi®" word mark and logos are registered trademarks owned by the Wi-Fi Alliance. Any use of these marks on this website does not imply any affiliation with or endorsement.